

Technical Information of Laja Travertine

	Type of test	Units	Standard Request	Rejection Number
1	Flexural Strength	Mpa	≥ 7.0	16,6
2	Dry Compressive Strength	Mpa	≥ 20.0	177
3	Bulk Density	g/cm ³	≥ 2.60	2,74
4	Water Absorption	%	≤ 0.75	0,23